



TECHNICAL DATA SHEET

Product name: PURE

Product type: Permeable precast concrete paver (PICP)

Geometric characteristics

Dimensions (in.): height x width x length (Dimensions include the joint)
3 1/8 x 9 x 9 (80 x 229 x 229 mm)
3 1/8 x 9 x 12 (80 x 229 x 305 mm)
3 1/8 x 9 x 15 (80 x 229 x 381 mm)

Joint width: 3/8 in. (10 mm)

Approximate weight: Variable 19.6 to 34.4 lb (8.9 to 15.6 kg)

Dimensional tolerances¹

Length and width: $\pm 1/16$ in. (1.6 mm)
Height: $\pm 1/8$ in. (3.2 mm)

Physical characteristics¹

Compressive strength: 8000 psi (55 MPa) (min)

Freeze-thaw durability

Loss of mass after 50 cycles: 1 % (max.)

Surface Infiltration characteristics

Percent of open surface area: 5 %

Surface Infiltration rate²: 726 in./hr (18 440 mm/hr)

Runoff Coefficient³: 0.25 (PICP on high infiltration soils)
0.40 (PICP on low infiltration soils)

Americans with Disabilities Act (ADA)

Surface slip resistance value⁴: slip-resistant surface texture

Surface opening⁵: joint opening size, 3/8 in. (10 mm)

Notes

1. Meets and exceeds the requirements of the ASTM C 936 Standard Specification for Solid Concrete Interlocking Paving Units.
2. Surface Infiltration rate measured as per ASTM C 1781.
3. Runoff coefficient values as per ICPI "Permeable Interlocking Concrete Pavements Design Manual, 4th edition".
4. Accessible paths shall be slip resistant. The above mentioned product is considered slip resistant and therefore complies with this ADA design guideline.
5. Accessible paths shall not allow the passage of a sphere greater than 1/2 in. (13 mm) in diameter. Pavers joint openings filled with aggregates comply with this ADA design guideline.

To learn more about the textures and colors for this product, please contact our representatives.

CANADA 5255, rue Albert-Millichamp, Saint-Hubert, QC J3Y 8Z8
USA 852 Pennsylvania Avenue, Pen Argyl, PA 18072
Telephone: 450 656-2992 / Toll free: 1 877 832-4625
Fax: 450 656-1983
www.techo-bloc.com

November 2015